



TEST REPORT

REPORT No.: CTB160824001C

Date: 2016-08-31

Page 1 of 3

Client Company: FORBEST MANUFACTURING CO.LTD

Address: 5FLOOR, HUASHUANG BUILDING, FULIAN INDUSTRIAL LONGHUA TOWN
SHENZHEN CITY GUANGDONG PROVINCE CHINA

Manufacturer's Name: FORBEST MANUFACTURING CO.LTD.

Address: 5FLOOR, HUASHUANG BUILDING, FULIAN INDUSTRIAL LONGHUA TOWN
SHENZHEN CITY GUANGDONG PROVINCE CHINA

Report on the submitted samples said to be:

Sample Name : LDPE TUBE
Style/ Item No. : /
Sample Receiving Date : 2016-08-27
Testing Period : 2016-08-28~2016-08-31
Results : Please refer to next page(s).

Summary of Test Results:

<u>TEST REQUEST</u>	<u>CONCLUSION</u>
FDA 21 CFR 177.1500-Maximum extractable fraction	Pass

Shenzhen CTB Testing Technology Co., Ltd

Add: First floor, E building, Huayang Technology Industry Park, Gushu Village,
Bao'an District, Shenzhen City, P.R.C
Web: <http://www.ctb-lab.com> Tel: +86-0755-61996588 Fax: +86-0755-23208027



TEST REPORT

REPORT No.: CTB160824001C

Date: 2016-08-31

Page 2 of 3

Test Result(s)

PART NAME No.1: LDPE TUBE

FDA 21 CFR 177.1500-Maximum extractable fraction

Test Requested: As specified by client, to determine Maximum extractable fraction Nylon 66 used in Contact with Food and Drug Administration Regulations.

Test Method: With reference to US FDA 21 CFR 177.1500.

(1)

Time	Temperature	Max..Permissible Limit	Result of 001	Comment
8hr(s)	Reflux temperature	0.2% (w/w)	<0.05% (w/w)	PASS
8hr(s)	Reflux temperature	1.5% (w/w)	0.35% (w/w)	PASS
8hr(s)	Reflux temperature	1.5% (w/w)	0.32% (w/w)	PASS
8hr(s)	Reflux temperature	0.2% (w/w)	<0.05% (w/w)	PASS

Note:

1. MDL = Method Detection Limit
2. " - " = Not Regulated


Check By:

Mason Lai

Approve By:



Date: 2016-08-31

Photo documentation

*** End of Report ***